






MITOP, akciová společnost Papírenské plstěnce řady VLP VLP 95



VLP 95 950 g/m²

VLP 95/2	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 6,7/80 25% 11/80 50% 17/80	
VLP 95/3	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 3,1/80 25% 6,7/80 50% 11/80	
VLP 95/4	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 6,7/80 25% 11/80 25% 17/80 25% 22/80	
VLP 95/4S	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 11/80 hrubé 25% 17/80 25% 22/80 25% 44/80 jemné 25% 3,1/80 50% 6,7/80 25% 11/80	
VLP 95/5	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 11/80 25% 17/80 25% 22/80 25% 44/80	
VLP 95/6	podkladová tkanina 335 g/m ² osnova: PAD 0,2/2x2 útek: PAD 0,2/2x3	vlákenné rouno 615 g/m ² 25% 11/80 25% 17/80 25% 22/80 25% 44/80	